



Acryrub N

Revision: 20/07/2016 Page 1 from 2

Technical data

Basis	Acrylic dispersion
Consistancy	Paste
Curing system	Physical drying
Skin formation* (20°C / 65% R.H.)	Ca. 20 min
Density	Ca. 1,66 g/ml
Maximum allowed distortion	15 %
Temperature resistance	$ -20 \degree C \rightarrow 80 \degree C$
Application temperature	$5 ^{\circ}\text{C} \rightarrow 30 ^{\circ}\text{C}$
Shrinkage	Ca. 15% (DIN 52451)

^(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

Acryrub N is a high-quality, plasto-elastic onecomponent joint sealant based on acrylic dispersions.

Properties

- Very easy to apply
- · Colourfast and waterproof after curing
- Can be painted over after curing
- Very good adhesion on many porous surfaces and aluminium

Applications

- Joints with movement till max. 15%
- Connection joints in building industry.
- Joints on window sills, between plinths and walls, between masonry, ...
- Filling of cracks in concrete and plasterwork.

Packaging

Colour: white, grey, brown, black Packaging: 280 ml cartridge

Shelf life

At least 12 months in unopened packaging in a dry storage place at temperatures between +5°C and +25°C. Protect against frost.

Substrates

Substrates: all common porous surfaces in construction and renovation. Not suitable for natural stone, bitumen, glass and metal. Nature: the substrates to be sealed must be clean, dry and free of dust. Surface preparation: Highly porous surfaces should be primed with diluted Acryrub N (1 part Acryrub N + 2 parts water). We recommend a preliminary adhesion test on every surface.

Joint dimensions

Min. width for joints: 5 mm

Max. width for joints: 20 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = joint depth. Use PE backer rods before applying the sealant in large joints to avoid 3-point adhesion.

Application method

Do not apply when rain or frost is imminent during curing process.

Application method: Apply the sealant by means of a manual or pneumatic caulking gun into the joint. Next finish with for example a filling-knife.

Cleaning: Before curing, Acryrub N can be removed with water from substrates and tools. Finishing: With a soapy solution or Soudal Finishing Solution before skinning. Repair: With the same material

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 BE-2300 Turnhout

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com





Acryrub N

Revision: 20/07/2016 Page 2 from 2

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the label for more information.

Remarks

- Do not use in applications where continuous water immersion is possible.
- Paintable with most paints.
- The paint must be sufficiently elastic to allow application on a plasto-elastic sealant.
- Given the great diversity in available paints it is recommended to do a compatibility test prior to application.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 BE-2300 Turnhout

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com